ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E).,Songjiang
Shanghai China
Postal Code: 201613
Tel:(021)57747878
Fax:(021)51685279
Website: https://www.escort.com.cn/CN

TEST REPORT

MATERIAL : NBR 90 DURO RED

COMPOUND NO: N9001R

Physical Properties (Press Cure:170℃X10min Post Cure:150℃X1h)	Requirement	Test result
Hardness,Point 硬度(邵A)	85.00~95.00	92.00
Tensile Strength,min,Mpa 拉力強度	7.00	10.70
Ultimate Elongation,min,% 延伸率	100.00	161.00
Specific Gravity, 比重		1.55
Heat Resistance 70h@100℃ 老化試驗		
Change in hardness,max,Point 硬度變化(邵A)	+15.00	-2.00
Change in tensile strength,max,% 拉伸強度變化率	-20.00	+2.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-40.00	+4.00
Compression Set 22h@100℃ 壓縮永久變形試驗		
Compression set,Method B,max,% 壓縮永久變形	25.00	19.00
Fluid Resistance No.1 Oil Resistance 70h@100℃ 1號油試驗		
Change in hardness,Point 硬度變化	-5.00~15.00	-2.00
Change in tensile strength,max,% 拉力強度變化率	-25.00	+8.00
Change in ultimate elongation,max,% 延伸率變化率	-45.00	+2.00
Change in volume,% 體積變化率	-10.00~5.00	-1.00
Fluid Resistance No.3 Oil Resistance 70h@100℃ 3號油試驗		
Change in hardness,Point 硬度變化	-20.00~0.00	-13.00
Change in tensile strength,max,% 拉力強度變化率	-45.00	-5.00
Change in ultimate elongation,max,% 延伸率變化率	-45.00	+4.00
Change in volume,% 體積變化率	0.00~35.00	+13.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY

THIS COMPOUND N9001R CAN MEET ASTM 2000 M6BG907A14B14EO14EO34



QA Manager: Dabou Ku **QC.Dept:** LingLing.Li **Test by:** QC08