

TEST REPORT

MATERIAL : NBR 70 DURO PAHS BLACK

COMPOUND NO: N7058B

Physical Properties (Press Cure:170°CX10min Post Cure:150°CX1h)	Requirement	Test result
Hardness,Point 硬度(邵A)	65.00~75.00	74.00
Tensile Strength,min,Mpa 拉力強度	10.00	15.90
Ultimate Elongation,min,% 延伸率	250.00	348.00
Specific Gravity, 比重		1.38

Heat Resistance 70h@125°C 老化試驗

Change in hardness,max,Point 硬度變化(邵A)	0.00~15.00	+4.00
Change in tensile strength,max,% 拉伸強度變化率	-25.00	-2.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-50.00	-29.00

Compression Set 22h@100°C 壓縮永久變形試驗

Compression set,Method B,max,% 壓縮永久變形	25.00	15.00
---------------------------------------	-------	-------

Fluid Resistance No.1 Oil Resistance 70h@125°C 1號油試驗

Change in hardness,Point 硬度變化	0.00~10.00	+2.00
Change in tensile strength,max,% 拉力強度變化率	-20.00	+9.00
Change in ultimate elongation,max,% 延伸率變化率	-35.00	-7.00
Change in volume,% 體積變化率	-15.00~5.00	-3.00

Fluid Resistance No.3 Oil Resistance 70h@125°C 3號油試驗

Change in hardness,Point 硬度變化	±10.00	-6.00
Change in tensile strength,max,% 拉力強度變化率	-15.00	-8.00
Change in ultimate elongation,max,% 延伸率變化率	-30.00	-9.00
Change in volume,% 體積變化率	0.00~25.00	+8.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND N7058B CAN MEET ASTM 2000 M2CH710A25B14EQ15EO35

