



The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd  
NO.205 Jiangtian RD(E).,Songjiang  
Shanghai China  
Postal Code: 201613  
Tel:(021)57747878  
Fax:(021)51685279  
Website: <https://www.escort.com.cn/CN>

## TEST REPORT

MATERIAL : EP 90 DURO BLACK

COMPOUND NO: E9001B

| Physical Properties (Press Cure:170°CX10min Post Cure:150°CX1h) | Requirement | Test result |
|-----------------------------------------------------------------|-------------|-------------|
| Hardness,Point 硬度(邵A)                                           | 85.00~95.00 | 91.00       |
| Tensile Strength,min,Mpa 拉力強度                                   | 10.00       | 15.90       |
| Ultimate Elongation,min,% 延伸率                                   | 100.00      | 137.00      |
| Specific Gravity, 比重                                            |             | 1.18        |
| Heat Resistance 70h@125°C 老化試驗                                  |             |             |
| Change in hardness,max,Point 硬度變化(邵A)                           | +10.00      | +0.00       |
| Change in tensile strength,max,% 拉伸強度變化率                        | -20.00      | +13.00      |
| Change in ultimate elongation,max,% 扯斷伸長率變化率                    | -40.00      | -28.00      |
| Compression Set 22h@125°C 壓縮永久變形試驗                              |             |             |
| Compression set,Method B,max,% 壓縮永久變形                           | 70.00       | 57.00       |

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY  
THIS COMPOUND E9001B CAN MEET ASTM 2000 M7CA910A25B35

